

Hyflon® AD 60

perfluoropolymer

Hyflon® AD 60 is an amorphous perfluoro-polymer available in powder form.

Hyflon® AD polymers resemble semicrystalline perfluoropolymers in their performance properties as they exhibit high temperature stability, excellent hydrophobicity and chemical resistance as well as very low surface energy.

Key distinctive feature of Hyflon® AD polymers is that they are soluble in selected solvents. In particular, their high solubility in perfluorinated solvents and their low solution viscosities make them suitable for solution process technologies.

Hyflon® AD can provide uniform and thin films or coatings (down to submicron thicknesses if required) by casting or coating techniques and thermal treatments, well below the

typical baking temperatures of semicrystalline perfluoro-polymers.

Examples of typical applications include membranes for gas separation and protective coatings.

Main features of Hyflon® AD 60 include:

- Amorphous glassy polymer structure
- Solubility in perfluorinated solvent
- Very high gas permeability and selectivity

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Amorphous • Chemical Resistant	• Good Thermal Stability
Uses	• Coating Applications	• Membranes
Forms	• Powder	
Processing Method	• Coating	• Solution Processing

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.93		ASTM D792
Intrinsic Viscosity (30°C)	0.50	dl/g	ASTM D2857

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	125	°C	ASTM D3418

Optical	Typical Value	Unit	Test method
Refractive Index	1.327		ASTM D542

Additional Information

Safety and Toxicology

- Before using Hyflon fluoropolymer resins consult the product Material Safety Data Sheet and follow all label directions and handling precautions.
- As with all fluoropolymer materials, handling and processing should only be carried out in well ventilated areas. Vapour extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact, wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapour or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods.

Storage and Handling

- Hyflon fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent dust contamination.
-

Notes

Typical properties: these are not to be construed as specifications.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.