

Technical Data Sheet
Type: Isoplast® 202EZ is an engineering thermoplastic resin.

Typical Properties	Test Method	English		S.I.	
		Values*	Units	Values*	Units
Physical					
Gardner 60° Gloss	ASTM D823	-	%	-	%
Mold Shrinkage	ASTM D 955	0.004-0.006	In/in	0.004-0.006	mm/mm
Water Absorption, 24 hours at 73°F (23°C)	ASTM D 570	-	%	-	%
Specific Gravity	ASTM D 792	1.20		1.20	
Mechanical					
Tensile Strength at Yield	ASTM D 638	10,000	psi	69	MPa
Tensile Strength at Break	ASTM D 638	9,000	psi	63	MPa
Elongation at Yield	ASTM D 638	9	%	9	%
Elongation at Break	ASTM D 638	90	%	90	%
Tensile Modulus	ASTM D 638	260,000	psi	1,800	MPa
Flexural Strength	ASTM D 790	13,000	psi	90	MPa
Flexural Modulus	ASTM D 790	320,000	psi	2,200	MPa
Izod Impact Strength	ASTM D 256	10	ft-lb/in	534	J/m
- Notched, 1/8" (3.2 mm), 73°F (23°C)		3	ft-lb/in	160	J/m
- Notched, 1/8" (3.2 mm), -40°F (-40°C)		-	ft-lb/in	-	J/m
Instrumented Dart Impact	ASTM D 3763	400	In-lb	45	J
- Total Energy at 73°F (23°C)		300	In-lb	34	J
Rockwell Hardness	ASTM D 785	-		-	
- R Scale		-		-	
- M Scale					
Thermal					
Deflection Temperature Under Load	ASTM D 648	260	°F	127	°C
- 66 psi (0.45 MPa), unannealed		290	°F	143	°C
- 66 psi (0.45 MPa), annealed		240	°F	116	°C
- 264 psi (1.8 MPa), unannealed		280	°F	138	°C
- 264 psi (1.8 MPa), annealed					
Vicat Temperature	ASTM D 1525	292	°F	144	°C
Coefficient of Linear Thermal Expansion	ASTM D 696	3.7	10 ⁻⁵ in/in/°F	6.7	10 ⁻⁵ mm/mm/°C
Optical					
Light Transmission	ASTM D 1003	-	%	-	%
Yellowness Index	ASTM D 1925	-	%	-	%
Processing Information					
Recommended Drying Temperature		260-280	°F	127-138	°C
Recommended Melt Temperature		460-500	°F	238-260	°C
Recommended Mold Temperature		200-250	°F	93-121	°C

*Typical values, not to be construed as specifications. Users should confirm results by their own tests.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.


<http://go.lubrizol.com/EP>

© 2018 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



<http://go.lubrizol.com/EP>